



## RUST-PRO 778

### 森帝 RUST-PRO 778 冷轧钢板静电喷涂防锈油

#### 简介：


A photograph showing a field of golden-brown crops, likely rapeseed, under a clear blue sky. In the distance, several white wind turbines are visible on a hill.

森帝 RUST-PRO 778 是一个高效能防锈剂，适用于冷轧带钢和钢卷的户内外存储防锈。森帝 RUST-PRO 778 具有极佳的水分驱除能力，可以在被保护的金属表面上形成一薄层油性膜，即使是在严厉的工况下如高湿度条件下也可有效的保护金属表面免受腐蚀。

A close-up photograph of a spray nozzle, likely used for electrocoat application. The nozzle is dark grey and is spraying a bright yellow liquid. The background is blurred, showing more of the spray.

森帝 RUST-PRO 778 在金属表面形成湿润的薄层油性膜，此膜无粘性，因此带钢表面涂覆后不会吸附灰尘及其他杂物，用于冷轧厂带钢和钢卷出厂前的预涂防护，森帝 RUST-PRO 778 可提供长达12个月的防锈期。

#### 特点和优点：

A close-up photograph of a spray nozzle, similar to the one in the previous image, spraying a bright yellow liquid. The nozzle is dark grey and is spraying a bright yellow liquid. The background is blurred, showing more of the spray.

森帝 RUST-PRO 778 可为冷轧带钢及钢卷提供经济有效的防锈保护，包括工序前及存储期间。本系列产品在严苛的存储环境下可对带钢及钢卷提供额外的抗磨保护，从而降低带钢表面的刮伤，减少退货率。

#### 应用场合：

森帝 RUST-PRO 778 适用于冷轧带钢及钢卷的防锈，也可用做精密加工零部件及仪器在存储期间的防锈保护。使用 RUST-PRO 778 防锈油可采用浸泡、喷雾和滚涂等方式使用，通常采用静电喷涂的方式用于冷轧钢板的预涂防锈。静电喷涂和过滤时温度不应低于 40°C。

## 产品典型技术指标：

性能	测试方法	<b>Rust-Pro 778</b>
颜色	目测	琥珀色
40 °C 粘度, cSt	ASTM D 445	13
倾点, °C	ASTM D 97	-9
闪点, °C	ASTM D 92	160
密度, g/cm <sup>3</sup>	ASTM D 1298	0.88
潮湿箱试验, 小时	ASTM D 1748	>480
盐雾试验, 小时	ASTM B 117	16

本产品简介系据当时的数据资料编写，所给数据资料均为典型代表值，允许有不影响其性能的轻微变化。用户应在其适用范围内使用本产品。

上海森帝润滑技术有限公司拥有以上所有版权。

Synnex Oil Co., Ltd.

<http://www.synnexoil.com>

20150302